

B8

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 61-268704

(43)Date of publication of application : 28.11.1986

(51)Int.Cl.

C08F 10/00

C08F 4/64

(21)Application number : 60-110654

(71)Applicant : MITSUBISHI PETROCHEM CO
LTD

(22)Date of filing : 23.05.1985

(72)Inventor : MATSUURA MITSUYUKI
FUJITA TAKASHI


(54) CATALYST FOR POLYMERIZATION OF OLEFIN

(57)Abstract:


PURPOSE: To provide the titled catalyst consisting of a combination of specific three components, exhibiting high activity as a Ziegler catalyst for the polymerization of an olefin, and giving a polymer having excellent polymer characteristics.

CONSTITUTION: The objective catalyst can be produced by combining (A) a solid composition consisting of (i) a product obtained by contacting a Mg dihalide, a titanium tetraalkoxide (or its polymer) and a polymeric silicon compound of formula I (R1 is hydrocarbon residue), (ii) an acid halide compound and (iii) a liquid Ti compound (the atomic ratio to the Mg compound of (i) is 0.1W10) and/or an Si halide (the atomic ratio to the Mg compound of (i) is 0.1W10),

wherein the molar ratio of the component (ii) to Ti is <0.1, with (B) an organic Al compound and (C) a heterocyclic compound having the principal skeleton of formula II (R2 is hydrocarbon group; R3WR6 are H or hydrocarbon group or two of them together form a ring; X is N or O).



I



II

LEGAL STATUS